

## CHEMICAL RESISTANCE

MEDIUM	AISI 1015 AISI 1085	AISI 52100	AISI 420	AISI 304	AISI 316
YOLK	A	A	A	A	A
MINERAL OILS	A	A	A	A	A
WATER	C	C	B	A	A
SALTED WATER	C	C	C	A	A
HYDROCARBONS	B	B	A	A	A
HYDROCHLORIC ACID	C	C	C	C	C
SULPHURIC ACID	C	C	C	C	B
NITRIC ACID	C	C	B	A	A
ALKALINE SALTS	C	C	B	A	A
VARIOUS FOOD	C	C	B	A	A
AMMONIA 30 %	B	B	C	A	A
FRUIT / JUICE	C	C	B	B	A
BENZENE	A	A	A	A	A
CHLORINATE HYDROCARBONS	B	B	B	A	A
CAUSTIC SODA	C	C	C	B	B
ETHER	A	A	A	A	A

**A = RESISTING**

**B = LIMITED RESISTANCE**

**C = NOT RESISTING**